



KUMHO PETROCHEMICAL

Kumho Chemical Laboratory, #1577 Yuseong-daero, Yuseong-gu, Daejeon, 305-348, Korea

polymer@kkpc.com, ykhwang12@kkpc.com

(TEL: 82-42-865-8685/8798, FAX:82-42-865-8797)

Mill Sheet

Product: STE2035

Color: BK

Property	Test	Unit	Spec.	Value
Tensile strength	EDS-T-7511	kg/cm ²	150	150
Tensile Elongation	EDS-T-7511	%	400	405
Flexural modulus	EDS-T-7510	kg/cm ²	5,500	5,500
Impact Strength Izod Notched 23 °C	EDS-T-7514	kg-cm/cm	NB	NB
HDT (0.45 MPa)	EDS-T-7520	°C	70	75
Specific Gravity	EDS-T-7406	g/cm ³	0.93±0.02	0.93
Hardness	EDS-T-7403		50±2	50
Melt Flow Index 195°C (5kg)	EDS-T-7516	g/10min	20	24