

KUMHO RM21 PRODUCT SPECIFICATION

Revision No. : 1

Issuing Date : Feb 05,2014

Revision Date : January 01, 2000

Spec. No. : D330-07-U31

ANALYSIS ITEMS	SPECIFICATION		TEST METHOD
	Min.	Max.	
VOLATILE MATTER (%)		0.50	ASTM D5668
ASH CONTENT (%)		0.80	ASTM D5667
ORGANIC ACID (%)	5.00	7.00	ASTM D5774
SOAP CONTENT (%)		0.50	
RAW MOONEY VISCOSITY, ML1+4 at 100 °C	37.0	45.0	ASTM D1646
COMPOUND MV VISCOSITY, ML1+4 at 100 °C		86.0	
TENSILE STRENGTH, Kgf/cm ²	35'	170	ASTM D3185 & D412
ELONGATION, %	35'	200	
200% MODULUS, kgf/cm ²	35'	130	
		180	

Note : 1. Vulcanizing condition : 145 °C X 35' Press vulcanizing

2. Carbon Black IRB # 7

J. W. Kang



jwkang@kkpc.com

General Manager, QA Team

Ulsan Sythetic Rubber Plant, Kumho Petrochemical