

KUMHO 1712G PRODUCT SPECIFICATION

Revision No. : 4

Issuing Date : Jun 25,2013

Revision Date : August 25, 2009

Spec. No. : D310-12-U31

ANALYSIS ITEMS	SPECIFICATION		TEST METHOD
	Min.	Max.	
VOLATILE MATTER (%)		0.50	ASTM D5668
ASH CONTENT (%)		0.80	ASTM D5667
OIL CONTENT (%)	25.8	28.8	ASTM D5774
ORGANIC ACID (%)	4.20	6.00	
SOAP CONTENT (%)		0.50	
BOUND STYRENE (%)	22.5	24.5	ASTM D5775
RAW MOONEY VISCOSITY, ML1+4 at 100 °C	49.0	55.0	ASTM D1646
TENSILE STRENGTH, Kgf/cm ² 35'	210		ASTM D3185 & D412
ELONGATION, % 35'	500		
300% MODULUS, kgf/cm ² 35'	90	130	

Note : 1. Vulcanizing condition : 145 °C X 35' Press vulcanizing

2. Carbon Black IRB # 7

J. W. Kang



jwkang@kkpc.com

General Manager, QA Team

Ulsan Sythetic Rubber Plant, Kumho Petrochemical