

KUMHO 1500NF PRODUCT SPECIFICATION

Revision No. : 2

Issuing Date : Aug 07,2013

Revision Date : October 01, 1999

Spec. No. : D310-16-U31

ANALYSIS ITEMS	SPECIFICATION		TEST METHOD
	Min.	Max.	
VOLATILE MATTER (%)		0.50	ASTM D5668
ASH CONTENT (%)		0.70	ASTM D5667
ORGANIC ACID (%)	5.00	7.00	ASTM D5774
SOAP CONTENT (%)		0.50	
BOUND STYRENE (%)	22.5	24.5	ASTM D5775
RAW MOONEY VISCOSITY, ML1+4 at 100 °C	47.0	55.0	ASTM D1646
COMPOUND MV VISCOSITY, ML1+4 at 100 °C		89.0	
TENSILE STRENGTH, Kgf/cm ²	35'	250	ASTM D3185 & D412
ELONGATION, %	35'	380	
300% MODULUS, kgf/cm ²	35'	140	

Note : 1. Vulcanizing condition : 145 °C X 35' Press vulcanizing

2. Carbon Black IRB # 7

J. W. Kang



jwkang@kkpc.com

General Manager, QA Team

Ulsan Synthetic Rubber Plant, Kumho Petrochemical