



KUMHO PETROCHEMICAL

Kumho Chemical Laboratory, #1577 Yuseong-daero, Yuseong-gu, Daejeon, 305-348, Korea

polymer@kkpc.com, ykhwang12@kkpc.com

(TEL: 82-42-865-8685/8798, FAX:82-42-865-8797)

Mill Sheet

Product: LEADCAP

Property	LEADCAP 64	LEADCAP 70	LEADCAP 76
Softening point (°C)	110	115	120
Viscosity at 140°C, cps	300	320	380
PG GRADE AP5 + LEACAP 2wt%	64-22	70-22	76-22