

SOL-5270H

Solution Styrene Butadiene Rubber (SSBR)

Product Introduction

- Kumho SOL-5270H is solution styrene butadiene rubber manufactured by anionic solution polymerization using alkyllithium initiator in organic solvent.
- It is non-oil extended clear SSBR.
- Its processibility, viscoelastic property and cold cold flexibility are superior to emulsion SBR.
- Kumho SSBR can be properly controlled in styrene %, Vinyl % and molecular weight and provides a wide range of styrene, vinyl and mooney level to optimize performance in variety of tire and industrial appli as it uses innovative coupling and funtionalizing technology.

Product Properties

Property	Typical value	Test Method
Styrene (%)	21	NMR MRTHOD
Vinyl (% in BD)	63	NMR METHOD
ML1+4 @100°C	67	ASTM D 1646
Tg (°C)	-25	ISO 11357-2
Oil content (%)	-	ASTM D 5774

Characteristics and Applications

- Typical application is for tire tread by mixing with NR, BR and any other rubber.
- Compatible with silica, as well as carbon black, so many advantage characteristics are observed in silica comj for tire tread such as increasing bound rubber, good filler dispersion, higher wet traction, lower rolling resistar lower heat build-up and lower mill shrinkage.
- SOL-5270H is functionalized to improve silica affinity by KKPC's innovative technology.

Manufacturer location

- Yeosu plant in Korea

Product safety

- Relevant safety data and references can be found in the safety data sheet.

Shelf life/Conditions

- 2 years from the production date at temperatures not exceeding 35°C, keeping away from direct sunlight, hum

Packaging

- Bale weight : 35kg (Wrapped by polyethylene film)
- Box weight : 1,050kg (30 bales)